## RARE PLANK HPD<sup>™</sup>

T E K N O F L O R<sup>®</sup>

CHEMICAL RESISTANCE January 2019

## ASTM F925 Resistance to Chemicals – Standard Test Method

	Surface Dulling		Surface Attack		Color Change	
Acids	<u>5 Minutes</u>	<u>24 Hours</u>	<u>5 Minutes</u>	<u>24 Hours</u>	<u>5 Minutes</u>	<u>24 Hours</u>
Acetic Acid- 28%	0	0	0	0	0	0
Citric Acid - 10%	0	0	0	0	0	0
Hydrochloric Acid- 10%	0	0	0	0	0	0
Sodium Hydroxide- 10%	0	0	0	0	0	0
Sulfuric Acid- 10%	1	1	0	0	0	0
Bases / Alkalis						
Ammonia 5%	0	0	0	0	0	0
Ammonium Hydroxide - 30%	0	0	0	0	0	0
Sodium Carbonate - 10%	0	0	0	0	0	0
Alcohols						
Ethyl (Denatured) Alcohol - 90%	0	0	0	0	0	0
Hand Sanitizer (Alcohol Based)	0	0	0	0	0	0
Rubbing Alcohol (70% Isopropyl)	0	0	0	0	0	0
Aromatics						
Crude Oil	0	0	0	0	0	0
Fuel Oil #1	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Phenol	1	1	0	0	0	0
Mineral Oil	0	0	0	0	0	0
Mineral Spirits (White Spirit)	0	0	0	0	0	0
Turpentine	1	1	1	1	0	0
Unleaded Gasoline (Regular Grade)	0	Ο	0	0	0	Ο
Hospital Chemicals						
Aniline Blue- 2.5	0	0	0	0	0	0
Betadine Skin Cleanser	0	0	0	0	0	0
Betadine Solution - 10%	0	0	0	0	0	0
Blood	0	0	0	0	0	0
Disclosing Solution (to show plaque on teeth)	0	0	0	0	0	0
Formaldehyde- 37%	0	0	0	0	0	0
Hematoxylin	0	0	0	0	0	0
Iodine Tincture	0	0	0	0	1	1
Iodine Gram Stain	0	0	0	0	1	1
Methylene Blue	0	0	0	0	0	0

	Surface Dulling		Surface Attack		Color Change	
Hospital Chemicals (Cont.)	<u>5 Minutes</u>	24 Hours	<u>5 Minutes</u>	24 Hours	<u>5 Minutes</u>	24 Hours
Potassium Permanganate- 1.5%	0	0	0	0	2	2
Silver Nitrate - 5%	0	0	0	0	0	0
Tincture of Benzoin	0	0	0	0	0	0
Urea Solution	0	0	0	0	0	0
Wright's Blood Stain	0	0	0	0	0	0
<u>Cleaners / Disinfectants</u>						
A456 II Germicide	0	0	0	0	0	0
Acetone - High Solvency	0	0	0	0	0	0
Bleach 5%	0	0	0	0	0	0
Bleach 10%	0	0	0	0	0	0
Ecoshine Stainless Steel Polish	0	0	0	0	0	0
Lemon Eze Cream Cleanser	0	0	0	0	0	0
Lime A Way	0	0	0	0	0	0
QC 52 Glass Cleaner	0	0	0	0	0	0
QC 53 General Purpose Cleaner	0	0	0	0	0	0
QC 31 Neutral Cleaner	0	0	0	0	0	0
Quaternary Disinfectant Cleaner	0	0	0	0	0	0
Phenol Disinfectant Cleaner 5%	0	0	0	0	0	0
Other Staining Agents						
Ball Point Pen	0	0	0	0	0	0
Bicarbonate	0	0	0	0	0	0
Hot Coffee	0	0	0	0	0	0
Cola Soda	0	0	0	0	0	0
Hair Dye	0	0	0	0	1	1
Olive Oil	0	0	0	0	0	0
Permanent Marker	0	0	0	0	0	0
	0	0	0	0	0	0
Printer Toner						
Red Kool Aid	0	0	0	0 0	0	0
Red Wine	0		0		0	
Shoe Polish Paste Brown	0	0	0	0	0	0
Tar Valley Mysteral	0	0	0	0	0	0
Yellow Mustard	0	0	0	0	0	0

Ratings Key:

0 – No Change

1 - Slight Change

2 - Moderate Chante

3 – Severe Change