TEKNOFLOR®

HIGH PERFORMANCE FLOORING



FORESTSCAPES HPD[™]

MODERN COLLECTION . COORDINATING LUXURY VINYL SHEET . HIGH PERFORMANCE DESIGN

TRADITIONAL LOOK. MODERN COMPOSITION.

Teknoflor[®] Forestscapes HPD[™] Modern Collection of Commercial Resilient Sheet was designed to offer your favorite traditional wood looks from our most tenured Teknoflor collection in a modern composition made of 100% virgin vinyl and free of phthalates. Teknoflor Forestscapes HPD sheet vinyl coordinates with our popular Teknoflor Forest plank Luxury Vinyl Plank collection for added versatility and design. Our hardest working floor is now even tougher and more thoughtfully made to meet your standards and exceed your expectations for a beautiful, clean wood look to last for years to come. For more information, contact your Teknoflor sales representative.



DURABLE AND LOW MAINTENANCE	 No Wax, No Buff, and no sealers or finishes needed; easily cleaned by damp mopping or auto-scrubbing Thicker 2.3mm gauge for enhanced performance in heavy traffic areas Maintenance savings result in investment payback in approximately two years
ENVIRONMENTALLY FRIENDLY	 No buff floors mean no bacteria, dust or wax particles are thrown into the air during cleaning No odors from floor finishes or strippers; no wax flushed into sewer system Complies with REACH requirements for Substances of Very High Concern Made with 100% Virgin Vinyl Floorscore Certified
SAFE	ADA CompliantApproved for emergency egress areas - NFPA 101
OVERALL THICKNESS	• 2.3mm (0.091")
WARRANTY	• 12-year commercial warranty
APPLICATIONS	 Ideal for Healthcare, Senior Living, Retail, Corporate/Office, Academic and Hospitality Environments

FORESTSCAPES HPD[™] | TEKNOFLOR[®] |







88056 Cinnamon



88057 Buck



88058 Brandy



88059 Natural



88060 Light Fawn



88061 Tanned



88062 Mulch



88063 Dawn



88064 Dusk



88065 Russet



88066 Eagle





88067 Sepia

88068 Fog



88069 Steel



88070 Firewood



88071 Tawny



88072 Charcoal



88073 Raven



88074 Sunrise



88075 Flame



88076 Amber

TEKNOFLOR FORESTSCAPES HPD

MODERN COLLECTION . COORDINATING LUXURY VINYL SHEET . HIGH PERFORMANCE DESIGN

PRODUCT DATA		PACKAGING	
STANDARD SPECIFICATION	ASTM F1303 - Meets or exceeds requirements		6' Wide (1.82m) x 75' Long (22.86m)
CLASSIFICATION	Type I, Grade 1	DIMENSIONS	
BACKING CLASS	Class A	ROLL SIZE	50 SY (450 Sq. Ft.)
COMPOSITION	Virgin PVC, No outside recycled content and Phthalate Free	WEIGHT	295 lbs.
TOP COAT	HP Urethane Coating with Ceramic Bead		
WEAR LAYER THICKNESS	0.50 mm (20 mils or 0.020 in)		
OVERALL THICKNESS	2.3mm (0.091")		

PERFORMANCE SPECIFICATIONS	TEST METHOD	STANDARD REQUIREMENT	RESULT
CHEMICAL RESISTANCE	ASTM F925	0- No change or 1 - Slight Change	0 - No Change
HEAT STABILITY COLOR CHANGE	ASTM F1514	ΔE < 8.0 avg. @ 7 days	Passes
LIGHT STABILITY COLOR CHANGE	ASTM F1515	Δ E < 8.0 avg. @ 300 hrs.	Passes
SHORT TERM INDENTATION	ASTM F1914	avg. < 8.0 avg. @ 50 lbs	avg. 3.6% 0.003"
STATIC LOAD LIMIT	ASTM F970	250 psi \leq 0.005" Residual Indentation	Exceeds Requirements 1,000 psi at maximum limit
FLOORSCORE	Certified		SCS-FS-04567
HEAVY METALS	ASTM F963		No concern with heavy metal content
ABRASION RESISTANCE	ASTM D4060	H18 Wheel & 1 kg mass applied	32,000 cycles to see effect on design layer
PHILLIPS CASTOR CHAIR TEST	Phillips Castor Chair Test	150 lbs. Load / Rating Scale 1-5 / 5-No Change / 1 - Severe Change	20,000 Cycles-5-Excellent No Change
REACH -Substances of Very High Concern (SVHC)	Test for EU REACH Chemi- cals of Concern	SVHC's tested must be less than 0.1% by product weight	Passes

SAFETY PERFORMANCE	TEST METHOD	STANDARD REQUIREMENT	RESULT	
STATIC COEFFICIENT OF FRICTION (SCOF)	D2047	≥ 0.5 SCOF Dry	≥ 0.6 SCOF Dry	
DYNAMIC COEFFICIENT OF FRICTION (DCOF)	ANSI B101.3	Low/Acceptable/High Traction - Wet DCOF	High Traction - Wet DCOF	
CRITICAL RADIANT FLUX	E648	Class I: \geq 0.45 w/cm2 Class II: \geq 0.22 w/cm2	Class I	
SMOKE GENERATION	E662	<450 Flaming	<450 Flaming & Non-Flaming	
APPROVED FOR EMERGENCY EGRESS AREAS - NFPA 101				

