

MATERIAL: PLANK YOU VERY MUCH™

- Commercial Resilient Sheet
- NO WAX NO BUFF...EVER
 - Gauge: 2.3 mm (0.90")
 - Width x Length: 6 feet x 75 feet
 - Packaging: 50 SY Per Roll
 - Weight: 6.6 lbs. per SQ YD

WARRANTY: 12 Year Non-Prorated Warranty. Company will furnish replacement flooring free of charge for TUF STUF Plank You Very Much if there is a loss of original pattern and color under normal commercial use of TUFSTUF for Twelve (12) years from date of installation, provided the flooring was installed and maintained according to standards set by TUF STUF High Performance Flooring.

This Warranty shall include a reasonable amount of labor that is required for removing and reinstalling the replacement flooring. This Warranty does not include damage due to improper installation or maintenance, excessive moisture or alkalis in the subfloor or conditions arising from hydrostatic pressure, burns or loss due to inconvenience, incidental expenses or consequential damages. See warranty for complete coverage and exclusions. Company must be given the opportunity to inspect the installation and investigate the claim.

COLOR SELECTION: 17 wood grain SKU's

TEST DATA:

- Meets all requirements of ASTM F1303 Standard Specification for Sheet Vinyl Floor Covering with Backing
- Wear Layer: Type 1, Grade 1 embossed clear PVC wear layer of 20 mils.
- Backing Class: Class A: 4 ply fused backing system made of PVC layer, fiberglass inner layer, PVC inner layer & PVC backing layer
- ASTM D4060: Abrasion Resistance H-18 wheel & 1,000 gram mass applied - 18,000 Cycles until design layer visibly affected
- Critical Radiant Flux: ASTM 648: NFPA Class 1 (≥ 0.45 watts/cm²)
- Smoke Density: ASTM 662: <450 DM in flaming & non-flaming
- Static Load Limit: ASTM F970: Pass 1,000 psi at maximum limit
- Flexibility: ASTM F137 Pass
- Static Coefficient of Friction: ASTM D2047: ≥ 0.6 SCOF
- Chemical Resistance: ASTM F925: Pass No Staining

INSTALLATIONS:

- Moisture and pH testing shall be properly performed and documented to confirm subfloor suitability.
- Concrete: ASTM F2170 "In-situ Relative Humidity; ASTM F1869 Anhydrous Calcium Chloride; PH testing (ASTM F710); Wood: Calibrated Wood Pin Meter
- Install resilient flooring and accessories after other trades, including painting and overhead operations have been completed.
- Concrete: ASTM F2170 "In-situ Relative

INSTALLATIONS Cont'd:

- The substrate surface, floor covering and adhesive shall be at a consistent temperature between 65°F to 85°F (Min 68°F for Spray Adhesive) for 48 hours before, during and after installation.

ADHESIVE:

Use adhesives recommended by the flooring manufacturer.

APPROVED SUBSTRATES:

Properly prepared concrete, Thick Pour Gypsum (ASTM F2419), suspended wood and metal subfloors. Subfloor must be suitable for intended use and rigid, smooth and flat, permanently dry, clean & free of all foreign materials any other deleterious contaminants that may act as a bondbreaker or staining agent.

SURFACE PREPARATION: Use high quality Portland cement and or calcium aluminate based patching and leveling compounds recommended by their manufacturer for intended use conditions. The underlayment shall be mold, mildew and alkali resistant, non-shrinking and water-resistant with a minimum 3,500 psi cured compressive strength. Ensure proper mix water ratio, working time, drying time and moisture testing.

CAUTION: Gypsum patching compounds shall not be used unless recommended and warranted by product manufacturer as project compliant.

INSTALLATION PROCEDURES:

- Roll out resilient sheet flooring with top surface up. Allow material to relax for 24 hours
- Trim off all damaged ends
- Straight edge or underscore all side and end seams.
- Fold back sheet half way. Spread adhesive with replaceable blade type notched trowel. Roll sheet with downward pressure into adhesive.
- Roll sheet with 100-pound roller. Hand-roll all seams and perimeter of installation.
- Seams:
 1. Heat weld all seams
 - a. Groove seam to accept weld rod.
 - b. Melt matching/contrasting weld rod into grooves using heat weld gun.
 - c. Once the heat weld is completely cool, use guide plate on spatula or other weld trimming knife to skive the weld rod for the first pass. Trim the second pass without the guide plate to provide a smooth flush seam.
 2. Chemical weld all seams using manufacturer's approved low gloss chemical weld.

For complete installation instructions go to: TEKNOFLOR.COM

ROUTINE MAINTENANCE:

- Before beginning, read all safety warnings, wear appropriate protective gear and put out caution signs in the area to be cleaned.

ROUTINE MAINTENANCE Cont'd:

- Sweep, dust mop or vacuum the floor to remove all loose dirt and grit. Do not use treated dust mops.
- When available, clean the floor with an auto scrubber using a properly diluted Neutral pH cleaner and a 3M 5100 Red pad or equivalent pad or brush. Rotary or cylindrical brush cleaning is recommended for textured floors. DO NOT USE a more aggressive pad or brush.
- When an auto scrubber is not available, mop on a properly diluted Neutral pH floor cleaner. Apply the solution liberally, but do not flood the floor. Clean the floor using a mop, flat mop or machine scrub with a low speed (175-350 RPM) swing arm floor machine using a 3M 5100 Red pad or equivalent pad or brush. DO NOT USE A MORE AGGRESSIVE PAD OR BRUSH.
- Completely remove the cleaning solution using an auto scrubber, shop vacuum or mop and let the surface dry.
- Fans or air movers can speed up the drying process. Once the floor surface is clean and dry, remove caution signs.

FURNITURE RESTS & PROTECTORS:

- Use appropriate furniture rests and floor protectors under all chairs, furniture, rolling equipment and beds. Proper selection and care of furniture rests, wheels and floor protectors is an important part of effective floor care. Key elements include:
 - NON-STAINING: Be made of non-staining materials.
 - RADIUS EDGE: Provide slightly radius or rounded edges.
 - SUFFICIENT CONTACT AREA: Have a surface contact area that is large enough to evenly distribute the load without causing damage to the floor. Generally, a 1" or larger diameter flat smooth contact area is appropriate for most applications.
 - COMPOSITION OF FLOOR GLIDES: Commercial grade felt glides are preferred for resilient flooring. Stainless steel, nylon and non-staining rubber glides can be used. Do not use metal glides that may rust or plastic glides as they become abrasive with use and can scratch the floor.
 - COMPOSITION OF WHEELS: Wheels for resilient & hard surface flooring should have a soft tread compound of urethane or non-staining rubber. Do not use hard plastic or metal wheels or rollers on resilient flooring. Hard wheels can cause surface damage to the flooring and break the adhesive bond causing bubbling.

Always use floor maintenance equipment and products in accordance with the manufacturer's information. DO NOT use solvent-based cleaners, abrasive cleaners, pads or brushes or steel wool. These can scratch or dull the surface of the floor.

TUF STUF™ PLANK YOU VERY MUCH™ is a NO-WAX, NO BUFF product.