




CLEAN WOOD



7" x 48" | 177,8 x 1219,2 mm



Almond 1511



Dune 1512



Hazel 1513




Chestnut 1514



Charcoal 1515

CLASSIC WOOD



4" x 36" | 101,6 x 914,4 mm



Scandinavian Maple 1121




Canadian Maple 1122




Golden Oak 1142




American Cherry 1151



Antique Cherry 1171




Royal Quince 1161



Honduran Mahogany 1181



French Walnut 1101



Rosewood 1191

Philip J. Hughes
Fed Gov - DoD - GSA Account Manager
 937-829-8316
 phughes@teknoflor.com
 www.vip.vetbiz.gov
 SDVOSB GSA Schedule
 GS-27F-0036V VAMC VIP Verified
 CAGE Code: 4RRA8

UPOFLOOR®

www.upofloor.com

TECHNICAL DATA XPRESSION

ENOMER® -DESIGN PLANK AND TILE

RUSTIC WOOD

7" x 48" | 177,8 x 1219,2 mm



Smoked 1504



Natural 1503



Warm Grey 1501



Cool Grey 1502



Dark Grey 1505

GRAPHIC WOOD

7" x 48" | 177,8 x 1219,2 mm



White 1521




Black 1525




STRIPES

20" x 20" | 500 x 500 mm



Dark 1535



Light 1531

MOODS

20" x 20" | 500 x 500 mm



Marbled 1556



Faded 1551

TERRA

20" x 20" | 500 x 500 mm



Sand 1542





Limestone 1541



Earth 1544



Slate 1545

PRODUCT	Xpression	EN 14565	PVC- and plasticizer-free Enomer® flooring	
	Application	EN ISO 10874	23 / 34 / 43	
SPECIFICATION	Thickness	EN ISO 24346	~ 0.08" (2.0 mm)	
	Weight	EN ISO 23997	~ 0.70 lbs / sq ft (3400 g/m ²)	
	Size / Delivery packing • Classic Wood • Clean, Rustic, Graphic Wood • Moods, Stripes, Terra	EN ISO 24342	<ul style="list-style-type: none"> • ~ 4" x 36" (101.6 x 914.4 mm) / 30 sq ft (2.78 m²) / 30 pcs • ~ 7" x 48" (177.8 x 1219.2 mm) / 46.66 sq ft (4.33 m²) / 20 pcs • ~ 20" x 20" (500 x 500 mm) / 53.82 sq ft (5.0 m²) / 20 pcs 	
PRODUCT PROPERTIES	PROPERTY	TEST METHOD	RESULT	
	Indoor Air Certifications		Blauer Engel, M1, FloorScore, Austrian Ecolabel	
	Electrostatic Propensity	ATCC 134	< 2.0 kV	
	Slip Resistance DCOF (Wet)	ANSI B101.3	Acceptable	
	Slip Resistance SCOF (Dry & Wet)	ASTM C1028	≥ 0.7 Dry / Wet	
	Abrasion Resistance w weight loss	ASTM D 4060	~ 0.05 g	
	Castor Chair Test 25.000 cycles	EN 425	Pass	
	Critical Radiant Flux	ASTM E 648	≥ 0.45 W/cm ² Class 1	
	Smoke Density	ASTM E 662	≤ 450 Flaming & Non-flaming	
	Flexibility	ASTM F 137	Pass (1" mandrel)	
	Resistance to Heat	ASTM F 1514	Pass	
	Resistance to Light	ASTM F 1515	Pass	
	Short Term Indentation	ASTM F 1914	< 0.005" (6%)	
	Chemical Resistance	ASTM F 925	Excellence	
	Static Load Limit	ASTM F 970	Pass	
Static Load Limit	ASTM F 970 Mod	2000 psi		

UPOFLOOR AMERICAS | 940 Centre Circle, Suite 1000, Altamonte Springs, FL 32714 | 1 800 800 5247 | www.upofloor.com | sales@upofloor.com

Cleaning and maintenance instructions, see: www.upofloor.com



www.blauer-engel.de/uz120